



DECORATIVE WATER-BASED INTERIOR PRODUCT GROUP

BETEK CONCREATIVE **BETEK CONCRETE LOOK COATING**

PRODUCT DESCRIPTION

Betek Concreative is a decorative, acrylic-based, ready-to-use, colored plaster with exposed concrete look that can be applied on both interior and exterior surfaces, and shaped using a trowel.

SPECIFICATIONS

- Ready to use
- Waterproof and water-resistant
- Breathable
- Alkali-resistant
- Exposed concrete look
- Easy-to-apply

APPLICATION SURFACES

Ensure that the application surface is strong enough to support the product, smooth, stable, clean, dry and free of oil and dust. For interior concrete and plaster floors, prime using Betek Primer colored in the same color as the top coat, and apply Betek Concreative. For satin surfaces that might be poor bearing and easily deformable, paste the surface with Betek Interior Paste. Sand the pasted surface, prime with Betek Lux Primer, apply Betek Primer after coloring it in the same color as the top coat, and create a smooth surface. For plastered surfaces, other primers are recommended to be applied on Betek Gel Primer or Concentrated Primer for better adhesion.

For exterior concrete- or cement-based smooth surfaces, Betek Concreative can be directly applied on BetekSilan Primer or Betakril Primer.

Before applying on cracked surfaces, the wall cracks should be opened up in V shape and repaired by filling as required.

APPLICATION

Mix the product thoroughly using a low speed mixer immediately after opening the packaging lid and obtain a homogeneous mixture. Complete the surface preparations, apply the product on the surface smoothly using a steel trowel. Scrape off the excessive product from the surface in order to obtain a film layer as thin as the particles inside the product. Spread Betek Concreative to the surface homogeneously, and apply pattern in circular motions using a plastic, polyurethane or hard and smooth sponge trowel. Clean the patterning trowel frequently while applying pattern to the surface. Move steel trowel gently on the surface after patterning to obtain a smoother surface, if requested, and complete the process.

THINNING

Ready to use.

DRYING TIME (at 20°C, 65% RH)

Touch dry time: 1 hour

Application of second coat: none / 6 hours

Final drying: 24 hours

CONSUMPTION

Ranges between 1 - 1.5m² per kilogram for single coat depending on the absorption of the surface. Perform a controlled sample run to estimate the precise consumption.

PACKAGING

25KG

STORAGE May be stored for 3 years in its unopened packaging in a cool and dry environment protected against frosting and direct sunlight. Close the lid air-tight immediately after application.

Hazard Statement

H317 May cause allergic skin reactions.

Precautionary Statement

P101 If medical advice is needed, have product container or label at hand.

P102 Keep out of the reach of children.

P103 Read label before use.

P261 Avoid breathing dust/fume/gas/mist/vapor/spray.

P280 Wear protective gloves/protective clothing/eye protection/face protection.

P321 Specific treatment required (see label).

P363 Wash contaminated clothing before reuse.

P333+P313 If skin irritation or a rash occurs: Get medical advice/attention.

P501 Dispose of contents/container in accordance with local, regional, national and international regulations.

This technical sheet is prepared based on laboratory data at normal conditions. Consult technical personnel for details that are not provided above. Otherwise, the manufacturing company cannot be held responsible for failures that may arise due to lack of knowledge. Our company reserves the right to change this information. Where necessary, please refer to Material Safety Data Sheets for more information on health, safety and handling risks and precautions associated with the products.

This product is manufactured by Betek A.Ş. having the certificate of conformity to the standards TS EN ISO 9001, TS EN ISO 14001, TS 18001, TS EN ISO 50001, TS ISO 10002.