



DECORATIVE SYNTHETIC PRODUCT GROUP

Betek Matt Synthetic Paint

PRODUCT DESCRIPTION

Alkyd-resin-based, lead-free, matte, decorative interior topcoat paint.

SPECIFICATIONS

Matte appearance and the capability of superior covering and spreading on surfaces where it is applied. Does not leave brush and roller marks, or flow due to its easy-to-comb structure.

APPLICATION SURFACES

Used as protective and decorative topcoat paint on interior concrete, exposed concrete, plaster, concrete board, plaster board, OSB, MDF, wood, iron-steel-sheet metal surfaces with suitable primers.

APPLICATION

Ensure the application surface is smooth, secure and in a well condition to hold the primer and the top-coat paint. Clean all types of stain, rust, dust, block grease, loose layers and make the required surface corrections. Comply with the defined setting periods on concrete, brute concrete and new plastered surfaces (28 days).

Sand the surfaces using fine grained emery paper before starting to apply primer on old painted water-solvent based surfaces. Clean the surface after sanding, apply a synthetic primer.

Wood (solid) surfaces: Apply Betek Impregnation Care. Apply synthetic primer and repair with synthetic paste after Betek Impregnation Care if repair is required. Re-prime with synthetic primer after paste and move on to Betek Matt Synthetic Paint application.

New plastered surfaces: Apply Synthetic Primer on Betek Primer following scraping and sanding operations.

Dusting and/or very absorbent surfaces (plaster, lime, whitewash, low quality plastic painted surfaces, gas concrete): Avoid applying before combing/polishing with transparent primers (Betek 1/7 Concentrated Primer, Gypsum Primer) and applying synthetic primer. Apply Betek Matt Synthetic Paint as 2 coats after primer dries.

Iron, steel and sheet metal surfaces: Clean the surface and apply Betek Antirust in 2 coats. Metal surfaces like galvanized sheet, aluminum, copper zinc: Apply Betek Astarix and then apply Betek Matt Synthetic Paint.

Ensure the ambient and the surface temperature is between +5°C and +30°C during the application and until the product is fully dry, and protect the surfaces against frost. Apply using a brush, a roller or a sprayer. Apply in two coats with a roller or a brush, and wait for 24 hours between coats. Clean the tools used with Betek Synthetic Thinner immediately after application.

You can access the MSDS and TDS forms including the information regarding detailed application, healthy-safety-handling risks and precautions on www.betekexport.com.

For airless spraying:

Pressure : 140 bar

Nozzle Angle : 50°

Nozzle Size (inch) : 0.013"

Diluting : 10% (Volume)

THINNING

Thin by 5-10% using Betek Synthetic Thinner to achieve the consistency that can be applied with a roller or brush. It can be applied in single coat for airless applications, provided that the desired film thickness is provided by diluting with 10% Betek Synthetic Thinner. It should be noted that problems, such as rising, shrinking, cracking and drying, may occur on the surface for dilutions to be performed with thinners of different brand.

DRYING TIME (at 20°C, 65% HR):

Touch dryness: 2-3 hours

Final Coat Application: 24 hours (drying time can increase at higher relative humidity and lower temperature values)

Note: Maximum coverage is obtained when waiting-period is observed and the surface is primed.

CONSUMPTION

10-14 m² single coat per liter depending on the type, absorbency and structure of the application surface. Perform a controlled sample run to estimate the precise consumption.

**FLASH POINT**

43°C

STORAGE

May be stored for at least 3 years in its unopened packaging in a cool and dry environment protected against frosting and direct sunlight. To store the paint remaining in its packaging safely, some amount of thinner used must be added until the whole surface of the paint is completely covered or cover of the packaging must be closed firmly and fixed after twisted 180° for 1-2 times.

PACKAGING

15 L, 2.5 L, 0.75 L

HAZARD DESCRIPTION

Xn Hazardous to health.

Hazard statements

H226 Flammable liquid and vapour.

H304 May be fatal if swallowed and enters airways.

Precautionary statements

P101 If medical advice is needed, have product container or label at hand.

P102 Keep out of reach of children.

P103 Read label before use.

P210 Keep away from heat/sparks/open flames/hot surfaces. - No smoking.

P241 Use explosion-proof electrical/ventilating/lighting/equipment.

P301+P310 IF SWALLOWED: Immediately call a POISON CENTER or doctor/physician.

P303+P361+P353 IF ON SKIN (or hair): Remove/Take off immediately all contaminated clothing. Rinse skin with water/shower.

P405 Store locked up.

P501 Dispose of contents/

Ingredients identifying the hazard for labeling:

Solvent naphtha (petroleum), medium aliph.

This technical sheet is prepared based on laboratory data under normal conditions, consult to technical personnel for details that are not provided above. Otherwise, the manufacturing company cannot be held responsible for the failures that may arise due to lack of knowledge. Our company reserves the right to change this information.